

made some changes in this description, but the details are not known to the present authors. A careful analysis of the photographs of well oriented collagen show that the experimental data are not fully explained in terms of the above helix having  $c = 20 \text{ \AA}$ , but that they fit in well with a  $c$ -axis spacing of  $28.6 \text{ \AA}$ . The data observed are schematically indicated in Fig. 1, where the layers are arranged according to their  $l$ -value and the  $\xi$  values of the reflections found in each layer are indicated by their  $x$ -co-ordinate. The data refer to a stretched specimen of air-dried kangaroo tail tendon, for which  $c = 29.4 \text{ \AA}$ . The observed layer line spacings are shown on the right-hand side, and it will be noticed that they agree well with the calculated spacings, considering that the measurements are accurate only to about 5 per cent.

It is interesting that a reflection having a  $\xi$  value of approximately  $0.20$  is found in the fourth layer. The corresponding equatorial spacing is  $7.7 \text{ \AA}$  and the absence of a reflection with this spacing in the zero-layer line has led to some authors<sup>4</sup> questioning the hexagonal unit cell proposed by Pauling and Corey.<sup>5</sup> The existence of this spot in the fourth layer supports the assumption of a hexagonal unit cell made by Ramachandran and Kartha.<sup>1</sup>

It is found that the intensities of the reflections found in the various layers could be explained if the helices contain 10 residues in three turns, the spacing per residue being  $2.94 \text{ \AA}$ . The intensities of the various spots which occur in the different layers are theoretically proportional to  $J_n(2\pi R\xi)$ ,<sup>6</sup> where  $R$  is the radius of the helix and  $J_n(z)$  is the Bessel function of  $z$  of order  $n$ , and  $n$  takes the values given by the equation

$$3n + 10m = l, \quad (m \text{ being integral}).$$

The smallest value of  $n$  which is operative for each layer is also given in Fig. 1. It will be seen that (a) for values of  $l$  from 3 to 10, practically all the expected layers occur,

(b) all layers for which  $n = 0$  or 1 are observed to occur, (c) the spots corresponding to  $\xi = 0.14$  occur only in layers having  $n = 1$  or 0, and (d) when  $n > 2$ , no spots occur corresponding to  $\xi < 0.30$ . These facts are in good agreement with what is to be expected from theory.

Further, the smallest  $\xi$ -value at which spots are observed in each layer can be used to determine the order of magnitude of the radius  $R$  of the spiral. This comes out to be of the order of  $1 \text{ \AA}$ . On examining the various helical structures proposed so far for collagen,<sup>1,5,7-9</sup> the only structure for which the radius of the helix is of this order is the one described from this laboratory.<sup>1</sup> The helix in that structure contains three residues per turn, while the above analysis of the X-ray data indicates that the helix should contain  $3.33$  residues per turn. It may be mentioned that the calculated density agrees much better with the experimental value with  $3.33$  residues rather than with 3 residues per turn. Thus, a small modification of the earlier structure would appear to be in good agreement with the X-ray and other data for collagen. Such a modification is not likely to affect the main features of the structure and the details are being worked out in this laboratory.

1. Ramachandran, G. N. and Kartha, G., *Nature*, 1954, 174, 269.
2. Cowan, P. M., North, A. C. T. and Randall, J. T., *Nature and Structure of Collagen*, 1953, Butterworths, p. 241.
3. Cohen, C. and Bear, R. S., *J. Am. Chem. Soc.*, 1953, 75, 2703.
4. Randall, J. T., Fraser, R. D. B. and North, A. C. T., *Proc. Roy. Soc.*, 1953, 141B, 62.
5. Pauling, L. and Corey, R. B., *Proc. Nat. Acad. Sci. Wash.*, 1951, 37, 272.
6. Cochran, W., Crick, F. H. C. and Vand, V., *Acta Cryst.*, 1952, 5, 581.
7. Bear, R. S., *Advances in Protein Chemistry*, 1953, 7, 69.
8. Crick, F. H. C., *J. Chem. Phys.*, 1954, 22, 347.
9. Huggins, M. L., *J. Am. Chem. Soc.*, 1954, 76, 4046.

#### DR. K. R. RAMANATHAN

**DR. K. R. RAMANATHAN**, Director, Physical Research Laboratory, Ahmedabad, and Chairman, Atmospheric Research Committee, has been elected President of the International Union of Geodesy and Geophysics at the Tenth General Assembly Meeting held in Rome recently. His election to this high office is a gratifying recognition of his services to meteorology for nearly three decades, and is particularly well-timed in view of the global pro-

gramme for the Third International Geophysical Year now under way. The wide range of his interests is amply reflected in the variety of topics dealt with by him in his scientific publications; but among them special mention may perhaps be made of the study of thermal structure and movements of the upper air, in which field his contributions are outstanding. Our heartiest felicitations to him on the honour conferred on him.